



Product Description: Color Corrector

	Trade Name	INCI Name	Supplier	Formula #	Formula #	Formula #	Formula #	Formula #	Formula #
				207-68B	209-2A	209-2B	209-2C	209-2D	209-2E
A	PureSyn 2	Hydrogenated Polydecene	Sandream Impact	12.55	13.20	13.20	13.20	13.20	13.20
	Floramac 10	Ethyl Macadamiate	Floratch	24.90	26.20	26.20	26.20	26.20	26.20
	Jeesilc Ps-PTVL	Phenyl Trimethicone, Dimethicone/Vinyl Dimethicone Crosspolymer	Jeen	3.36	3.54	3.54	3.54	3.54	3.54
	Fanco ID-CG	Isododecane	Elementis	4.54	4.78	4.78	4.78	4.78	4.78
	Sansil D308	Dimethicone/Vinyl Dimethicone Crosspolymer	Sandream Impact	1.88	1.98	1.98	1.98	1.98	1.98
B	Micropoly 250S	Polyethylene	Micro Powders	4.58	4.82	4.82	4.82	4.82	4.82
	Candellilla Wax	Euphorbia Cerifera (Candellilla) Wax	Strahl & Pitch	2.96	3.12	3.12	3.12	3.12	3.12
	Synchrowax HR-C	Tribehenin	Croda	0.63	0.66	0.66	0.66	0.66	0.66
	Microcrystalline Wax	Microcrystalline Wax	Strahl & Pitch	2.01	2.12	2.12	2.12	2.12	2.12
C	SDI TiO2 AS	Titanium Dioxide, TES	Sandream Impact	17.97	10.00	10.00	10.00	10.00	9.05
	SDI Yellow IO AS	Iron Oxides Yellow, TES	Sandream Impact	1.88					
	SDI Red IO AS	Iron Oxides Red, TES	Sandream Impact	0.56					
	SDI Black IO AS	Iron Oxides Black, TES	Sandream Impact	0.18					
	Bichroma Yellow	Bismuth Oxchloride, Mica, Iron Oxides, Magnesium Stearate	Sandream Impact		7.35				
	Bichroma Violet	Bismuth Oxchloride, Mica, Manganese Violet, Magnesium Stearate	Sandream Impact			7.35			
	Bichroma Green	Bismuth Oxchloride, Mica, Chromium Hydroxide Green, Magnesium Stearate	Sandream Impact				7.35		
	Bichroma Red	Bismuth Oxchloride, Mica, Iron Oxides	Sandream Impact					7.35	3.46
	Majestic Rhubarb	Mica, Iron Oxides	Sandream Impact						4.84
	Zinc Stearate	Zinc Stearate	Brenntag	0.63					
D	PMAH	Polymethyl Methacrylate	Brenntag	6.89	7.25	7.25	7.25	7.25	7.25
	SanSilica 307	Silica	Sandream Impact	4.39	4.62	4.62	4.62	4.62	4.62
	SanTalc 511	Talc	Sandream Impact	5.00	5.00	5.00	5.00	5.00	5.00
	Benzophenone-3	Benzophenone-3	Sandream Impact	2.59	2.72	2.72	2.72	2.72	2.72
	Euxyl PE 9010	Phenoxyethanol, ethylglycerin	Schulke	1.25	1.32	1.32	1.32	1.32	1.32
	Vitamin E	Tocopheryl Acetate	Sandream Impact	1.25	1.32	1.32	1.32	1.32	1.32
TOTAL PERCENT				100.00	100.00	100.00	100.00	100.00	100.00

Procedure: Weigh all of phase A into glass beaker and heat to 90°C. Mix with propeller and continue mixing until all raws are dissolved and solution is homogenous. Mix phase B in a separate beaker at 95°C mix until all dissolved. Add phase B to A and continue mixing until uniform. Add C to AB while mixing with a homogenizer. Mix D in a separate beaker. Add phase D to the solution. Lower temperature to 70 °C. Pour into desired component.

The information provided is furnished without warranty, expressed or implied, except that it is accurate to the best knowledge of Sandream Impact LLC. Customers should utilize formulations provided as a guide and perform in-house stability, micro and other necessary testing.